

Our Ref: SW/LS

23 December 2020

Report 369521

Page 1 of 2

Lux Distribution Ltd
3 Watling Court
Ptarmigan Place
Attleborough Fields Ind Est
Nuneaton, Warwickshire
CV11 6GX

Contact: Ana Neale

DATE RECEIVED	:	11 DECEMBER 2020
DATE TESTED	:	21 DECEMBER 2020
QUALITY REFERENCE	:	CCF
SUPPLIER	:	LUX DISTRIBUTION LTD
REPUTED FIBRE CONTENT	:	NOT GIVEN
COLOUR/DESIGN	:	BLACK
FABRIC DESCRIPTION	:	FOAM

REQUEST: FMVSS 302 Determination of burning behaviour of interior materials in motor vehicles

RESULT: The sample submitted meets the requirements of FMVSS 302



S. WISEMAN
LABORATORY DIRECTOR



L. SMITH
FLAMMABILITY TECHNICIAN

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results.

FIRE TESTS ACCORDING TO FMVSS 302

Determination of burning behaviour of interior materials in motor vehicles

Procedure

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

Five specimens were tested in accordance with the above standard. The burning time and burnt distance were recorded and the burning rate, B, in millimetres per minute, calculated.

Requirements

Shall not burn at a rate of more than 102 mm per minute.

Results

The sample was tested in the as received condition, and in the length direction.

<u>Burn distance (mm)</u>	<u>Burning time (s)</u>	<u>Burn rate B</u> <u>mm/min</u>
SE	SE	/

SE = Self extinguished before start point.

Met the requirements of FMVSS 302.

